



日期 Date: 2019.06.20 收件日期 Date of Receipt: 2019.06.18 試驗報告 TEST REPORT 土城場區 TUCHENG

報告編號 Report No.: TFF8 數量 Quantity: 2件 報告頁次/頁數(P1/1) Page Order/Pages: 來文字號 Ref. No.: NIL

報告抬頭 Report Title: 試件類別 Item: 貼合布

地址 Address:

試驗項目	試驗結果		試驗方法
	A	B	
平均溫度(°C)	34.2	30.8	ASTM D7024-2004 (Modify) 熱流變化量(W/m <sup>2</sup> ):200 測試時間:10分鐘 環境溫度(°C):28

註：依委託者所提供來樣資料為：A. 5B仿蛋白質PU

B. 水性涼感PU

註：試餘樣品應委託人要求已隨本報告退還不再接受檢驗。

本試驗報告僅供參考，  
不做任何正式文件證明用



附記：1. 本報告僅對樣品負責，樣品保留期限為一個月。  
Note: This report is only responsible for the submitted sample(s), which will be kept for one month period.

2. 本報告非經本檢測及驗證部書面同意，不得摘錄複製，但全部複製除外。  
This report cannot be reproduced in any way, except in full context, without the prior approval in writing of this Department of Testing and Certification.

3. 試驗報告所載事項不得作為公開廣告及商業推銷之用。  
The test report should not be used for public advertisement and commercial promotion.

財團法人紡織產業綜合研究所  
所長授權核發人：  
Authorized by president of  
Taiwan Textile Research Institute



紡織產業綜合研究所檢測及驗證部 新北市土城區承天路6號  
Department of Testing and Certification, Taiwan Textile Research Institute  
No.6, Chengtian Rd., Tucheng Dist., New Taipei City 23674, Taiwan (R.O.C.)  
Tel : +886-2-22670321 ext. 7107, 7110  
Fax : +886-2-22675108, +886-2-22689839



TEST REPORT TUCHENG

Date: Jun. 20, 2019 Date of Receipt: Jun. 18, 2019

Report No.: TFF8 Quantity: 2PC Page Order/Pages: (P1/1) Ref. No.: NIL

Report Title: Item: Laminated Fabric


Address:

Test Items	Test Results		Test Methods
	A	B	
Average temperature (°C)	34.2	30.8	ASTM D7024-2004 (Modify) Heat Flux (W/m <sup>2</sup> ) : 200 Acclimation period : 10 minutes Environmental condition: 28°C, 65% R.H.

*This test report is for reference only and should not be used as a formal document.*

Note: Sample description is given by the client: A. 5B Wet PU  
B. Cool Eco PU-Water Based

Note: As the remaining sample was asked to return along with the test report, re-testing would not be possible.



- Note: 1. This report is only responsible for the submitted sample(s), which will be kept for one month period.  
2. This report cannot be reproduced in any way, except in full context, without the prior approval in writing of this Department of Testing and Certification.  
3. The test report should not be used for public advertisement and commercial promotion.

Authorized by president of  
Taiwan Textile Research Institute

*Gwo-Tsun Jou*

Director,  
Department of Testing and  
Certification

Department of Testing and Certification, Taiwan Textile Research Institute  
No.6, Chengtian Rd., Tucheng Dist., New Taipei City 23674, Taiwan (R.O.C.)  
Tel : +886-2-22670321 ext. 7107, 7110  
Fax : +886-2-22675108, +886-2-22689839